



STANDARD ENGINEERED PRO GOLD INFIELD MIX

1. Gradation – A minimum of 95% of particles shall pass the 2.00 mm sieve with the highest portion of sand particles in the course to medium range. Silt to clay ratio (SCR) shall be in the range of 1.5 -0. The final soil classification based on USDA criteria shall be a “sandy loam – sandy clay loam”.
2. “Reddish” in color.
3. For installation of new fields, place Pro Gold Infield Mix to a final minimum depth of 6 inches over a sub-base that is prepared to acceptable specifications. The final grade should be laser graded according to standard infield construction specifications. Allow for +/- 1 inch for compaction
4. For installation of existing fields, properly till the surface of the existing material while incorporating +/- 1 inch of Pro Gold Infield Mix. Continue placement of the remainder of Pro Gold Infield Mix that is to be installed.
5. After leveling the infield skin thoroughly, water the entire infield surface until the complete depth of the infield mix is moistened. After a period of +/- 4 hours compact with a minimum 2000 lb. static drum roller. If low areas are present, scarify and level low areas with additional Pro Gold Infield Mix.
6. Supplier – Gail Materials Inc www.gailmaterialsinc.com



MAILING ADDRESS:

11762 De Palma Road 1C-308
Corona, Ca 92883
Main Office: (951) 667-6106
www.gailmaterialsinc.com